

AC-620M

295grams/m²
MICROPERFORATED



TECHNICAL SPECIFICATIONS

PROPERTIES	DATA	LEGAL STANDARD
Weight	295 g/m ²	EN ISO 2286-2
Breaking strenght chain/fabric	1900 / 2000 N/50 mm	DIN 53354, DIN EN ISO 1421/VI
Breaking strenght warp/fabric	380 / 400 N	DIN 53363
Open Area	35%	LB 3.27
Resistance to cold	-20 °C	DIN 53361
Resistance to heat	+70 °C	LB 3.15
Breaking strenght seals	800 N/50 mm	DIN 53354
Trsnslucency	40%	at 550nm
Light fastness	>6 Note, Value	DIN 54004, DIN EN ISO 105 B02
Air Permeability	7520 l/m ² sec	DIN EN ISO 9237
Flame behaviour	DIN 4102: BI, NFP 92507: M2	

BASE FABRIC

Material	PES	DIN ISO 2076
Thread	1100 dtex	DIN ISO 2060

TYPE OF COATING

Coating	PVC
----------------	-----